

ITW PABCO CHILDERS

Stainless Steel Roll Jacketing

DESCRIPTION

ITW's Stainless Steel Roll Jacketing is manufactured from T-304 and T-316 prime grade Stainless Steels. These alloys comply with ASTM A-240, and are supplied with a regular 2D mill finish for reduced glare. The yield strength is 30,000-45,000 PSI and the tensile strength is 75,000-110,000 PSI. These alloys are of a special soft-annealed temper, for ease in fabrication. T-304 is normally used in all except the most corrosive areas, where T-316 is recommended.

The 300 series Stainless Steels have a melt point of approximately 2500°F, providing optimum fire protection. Stainless Steel has a higher emittance value than Aluminum, and has physical properties superior to all other metal used as insulation protective jacketing. T-304 contains 18% chromium and 8% nickel. T-316 contains 16.5% chromium, 10% nickel and 2.2% molybdenum.

Stainless Steel is available in smooth, stucco embossed, or 3/16" corrugated roll jacketing, and deep corrugated sheets. Jacketing is recommended for insulated piping, tanks, and vessels less than 8 feet in diameter. Deep corrugated sheets are recommended for diameters greater than 8 feet. It is recommended that the roll jacketing be 3/16" corrugated for the following reasons: it is stronger than smooth, it reduces glare from external light sources, it eliminates "coil break" when applied over small size piping and does not show dents readily. In extremely corrosive environments, smooth jacketing is recommended to facilitate run-off.

RECOMMENDED USES

Chemical Plants and Refineries:

Urea units, fertilizer plants, caustic facilities, petrochemical plants and aluminum refineries.

Steel Mills:

Coke ovens, oxygen steel making furnaces, by-product plants, aromatic plants and steam distribution facilities.

Paper Mills:

Digester areas, white and black liquor tanks, bleach tanks, chemical pulping and waste treatment tanks.

Miscellaneous:

Areas of high incidence of abuse on bridges, walkways and service roads, areas of high fire incidence, food processing facilities, packing plants and freeze facilities.

SUGGESTED SPECIFICATION

All insulation shall be weatherproofed with ITW's Stainless Steel jacketing. The jacketing is to be manufactured from T-304 (*T-316 option*) Stainless Steel with 3/16" corrugations (*or smooth option*) in .010 and .016" thickness (*.020 and .024 available*). All jacketing shall have an integrally bonded moisture barrier over the surface in contact with the insulation.